

Gyproc Xpert+ Stucco Gypsum Plaster

BP0014



Description

Gyproc Xpert+ is a stucco gypsum plaster made for application on almost all backgrounds, e.g. brickwork, block work or concrete, suitable for application like POP punning (over Sand & Cement Plaster), bull marks, level strips, etc. It has special additives for enhanced setting time helps in controlling the onsite wastages. It provides perfectly lined and leveled surface providing a perfectly flat surface ready for painting.

Features

- Extra whiteness
- Doesn't require water curing
- No shrinkage cracks
- Non-combustible (when tested in accordance with BS: 476: part 4:1970), therefore a good form of thermal protection to the building structure.
- With improved Thermal resistance properties. (Thermal Resistance $R = 0.07\text{m}^2\text{K/W}$ at 13mm thickness)
- GRIHA and Greenpro Certified.

Technical & Physical Parameters

Dry Bulk Density	880 Kg/m ³ (Max)
Wet Bulk Density	1.4-1.5 g/cm ³
Water To Powder Ratio	1:1.25
Setting Time	10-15 min

Chemical Composition

Calcium Sulphate Hemihydrate: $\text{CaSO}_4 \cdot \frac{1}{2} \text{H}_2\text{O}$

Drying Type

Setting

Identification & Packing

Xpert+ is packed in PP bags. The outer layer of the bag is printed with the product image, safety instruction, batch number, date of manufacturing, UOM, correspondence address and application instructions.

Available Sizes

20 kg & 25 kg

Gyproc Xpert+ Stucco Gypsum Plaster

BP0014



Shelf life time

Approx. 3 months from the date of manufacturing when stored in dry conditions.

Coverage

Applied Thickness	13 mm
Coverage*	22 sq-ft/25 kg bag

Standard Compliance

IS 2547 (Part I)-1976 for chemical characteristics

Application

Storage & Handling



Gyproc Xpert+ is supplied both in 25Kg & 20 Kg bags. The dimensions of the bag ensure that a well-filled appearance is presented when filled and the bags can be stacked on a pallet in a stable and well-stacked array. Bags should be stored dry, as absorption of water shortens the setting time, causes set lumps to form in the bags and may reduce the strength of the set plasterwork. No hooks or any sharp tools should be used to carry bags from one location to another.

Background Preparation

Surfaces should be reasonably dry, clean and protected from the weather, and suitable for the chosen specification. In addition, before plastering concrete backgrounds, ensure that any mould oil or other agents present are removed from the surface. No-fines concrete does not require wetting prior to plastering. Plaster should not be applied onto a 'green' background or when any free water is visible. Clean water should be applied 5-10 minutes before plaster application to control the suction. In-situ or pre-cast concrete which are exceptionally smooth or having low suction will require pre-treatment with Gyproc Bond-It bonding agent.

Mixing

Gyproc Xpert+ is mixed with only clean water for preparation. Mixing should be carried out in a clean tray or bucket. Excessive mechanical mixing should be avoided. Tools and water used in mixing must be clean. Contamination from previous mixes can shorten the setting time and in turn reduce the strength of the plaster when set. Water to plaster ratio (1 part of water: 1.25 part of plaster by weight) should be maintained to have good cohesive workable mix. Prepare plaster mix as much as required depending upon the immediate scope of work. Once the mix has begun to set, water addition is not recommended, as

Gyproc Xpert+ Stucco Gypsum Plaster

BP0014



performance properties of plaster will get altered, thus affecting workability, cohesiveness, adhesion properties and strength.

Application

Gyproc Xpert+ should be applied with firm pressure, built out to the required thickness, and ruled to an even surface and left as an undercoat to form a key for finish coat. A thin plaster mix is made and applied as a finish coat to provide smooth surface. It can be applied to an average thickness range of 3-15 mm on walls in one coat and up to 10 mm on ceilings. For punning S/C plaster surface should be wetted before application to provide firm bonding. After complete drying for usually 72 hours (depends upon thickness and weather conditions) the plain smooth leveled surface is ready for painting.

Tiling

Tiles up to 20 kg/m² can be applied directly to the Gyproc Xpert+ except where the system includes a bonding agent. Consideration should be given to tiling directly to the background. If plastering to provide a background for tiles avoid polishing the surface. Polished plaster surfaces should be roughened and a suitable primer used.

Precautions

- Dissimilar expansion and contraction of RCC and brick / stone masonry could cause stresses and at times separation. To reduce the separation cracks, use of 145 GSM glass fiber mesh (at the junction) is recommended.
- It is not suitable for use in long continuously damp or severely humid conditions.

Gyproc Xpert+ Stucco Gypsum Plaster

BP0014



Saint Gobain India Pvt Ltd - Gyproc® Business reserves the right to revise product specification without notice. The information herein should not be read in isolation as it is meant only as guidance for the user, who should always ensure that they are fully conversant with the products and systems being used and their subsequent installation prior to the commencement of work.

*Above parameters are tested under lab conditions. Actual performance depends on site usage, conditions and working.